

PAVIFER-313

Two-component, 100% solids, moisture-blocking epoxy primer for concrete substrates, cement coatings and mortars.

- For substrates with moisture.
- Primer for the application of liquid waterproofing membranes.
- As a fixative primer layer for subsequent finishes.
- As a surface fixer.
- Binder for leveling mortars and coating mortars.



PRODUCT DESCRIPTION

PAVIFER-313 is a solvent-free, 100% solids moisture-blocking primer.

RECOMMENDED USES

PAVIFER-313 is a primer for priming concrete substrates, cement coatings and epoxy mortars.

- For substrates with moisture.
- Primer for the application of liquid waterproofing membranes.
- As a fixative primer layer for subsequent finishes
- As a surface fixer
- Binder for leveling mortars and coating mortars.
- As a fixative primer layer for subsequent finishes

FEATURES & BENEFITS

It eliminates the formation of soil dust, improves its surface hardness, prevents erosion and wear, facilitating the adhesion of other coatings. The main features and benefits of the **PAVIFER-313** are as follows:

- Low viscosity
- Good penetration
- Excellent adhesion
- Solvent-free
- Easy to apply
- Short waiting times
- Multifunctional
- Easy to apply

PRESENTATION

PAVIFER-313 **primer** is available in 10 kg metal kits.

Component A (Base):	6 Kg.
Component B (Catalyst):	4 Kg.

STORAGE CONDITIONS

12 months from the date of manufacture, in its original containers, well closed and not damaged. Store in a dry place at temperatures between +5° C and +30°.

Sheet

PAVIFER-313

EEdition: January

Page 3 of 5

TECHNICAL DATA

Chemical Basis	Epoxy
Aspect:	Satin
Color:	Incolí
Solid Volume:	100 %
Yield:	5 - 8 m ² / kilo
Specific Gravity:	1,300 +/- 0,020 Kilos / Litro
Dry to the touch:	10 hours at 20° C and 60% relative humidity
Commissioning:	48 hours people 72 hours light vehicles 7 days full use
Flash Point:	22° C
COV's:	Complies with Directive 2004/42/EC (RD 22/2006) Annex I subcategory j): 304.8 g/l (500 g/l maximum as of 01.01.2010).

PRODUCT PREPARATION

- Mix the two components using a low-speed stirrer.
- If the application is made at high temperatures, the life of the mixture can be significantly reduced.
- Drying and hardening time will depend on the ambient temperature and humidity during application.
- If a rough finish with non-slip properties is desired, sprinkle on the first coat freshly
- Applied fine silica arena.
- For the treatment of non-concrete pavements, please consult our Technical Department
- Preserve the container from frost and direct sun exposure before mixing, shake component A in its container and then add component B mixing for 2 to 3 minutes until the resulting product is completely homogeneous.
- To ensure correct mixing, pour into an empty container and continue kneading until homogenized. Avoid overmixing to minimize the amount of occluded air.

CONDITIONS OF APPLICATION

Catalyst:	Catalyst PAVIFER-313
Mixing Ratio:	2.33 to 1 in volume
Mix Life:	6 hours at 20° C
Method:	Airless brush, roller or gun
Dilution:	Epoxy solvent (maximum 10%)
Espesor:	Húmedo: 150 micras Seco: 150 micras
Refinish Interval:	Minimum: 24 hours at 23° C Maximum: 3 days at 23° C
Conditions:	Apply at temperatures above +10° C and relative humidity below 80%. The temperature of the paint and surface must be above this limit.

Sheet

PAVIFER-313

*E*dition: January

APPLICATION DETAILS

Quality of support	The concrete substrate must be compact and have minimum compressive strengths of 25 N/mm ² and tensile strength of 1.5 N/mm ² . The substrate must be clean, dry and free of all types of contaminants, such as oils, greases, coatings and surface treatments, etc. When in doubt, apply a test area.
Preparing the Stand	Concrete substrates must be prepared by mechanical means (sanding, shot blasting or scarified) in order to remove surface grout and obtain an open-pore, textured surface. The weak parts of the concrete must be eliminated and all possible defects in the substrate must be discovered. Support repairs, hollow filling, and bracket leveling are all with appropriate products. The substrate must be primed or leveled to obtain a compact surface. Large stains should be removed by sanding. All dirt as well as loose or poorly adhered parts should be removed before application, preferably by sweeping or vacuuming.
Temperature of the support	Minimum + 10 °C / Maximum + 30 °C
Ambient Temperature	Minimum + 10 °C / Maximum + 30 °C
Substrate humidity	≤ 6% by weight Measured with method, CM gauge or kiln drying method. There should be no rising damp according to the ASTM standard (polyethylene sheet).
Relative humidity	Maximum 75% r.h. Proper ventilation should be ensured to remove excess of moisture during curing.
Dew point	Watch out for condensation! The substrate and ambient temperature should be at least 3°C above the Dew Point during application.

CURING DETAILS

Ready-to-Use Applied Product	From 2 min to 24 hours. The times are approximate and may be affected by the environmental conditions, especially temperature and relative humidity.
Note	All technical data given in this Product Data sheet are based on laboratory tests. Actual measurements of this data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the operation of this product may vary from country to country. Please refer to the local Data Sheet for the exact description of the fields of application.
Safety Instructions and Hygiene	For any information regarding safety issues in use, handling, storing, and disposing of chemical residues, users should refer to the most recent version of the Product Safety Data Sheet, which contains physical, ecological, toxicological and other related data safety.

LEGAL NOTICES

This information and, in particular, the recommendations regarding the application and end use of the product are given in good faith, based on the current knowledge and experience of POLIUREA SISTEMAS of the products when they are correctly stored, handled and applied, in normal situations, within their useful life, in accordance with the recommendations of POLIUREA SISTEMAS

In practice, the possible differences in materials, substrates and actual conditions at the place of application are such that no warranty in terms of merchantability or fitness for particular purposes, nor any obligation whatsoever outside of any legal relationship that may exist, can be inferred from the information herein, nor from any other written advice or advice offered.

The user of the products must carry out the tests to check their suitability according to the use they want.

they want to give it to him. POLIUREA SISTEMAS reserves the right to change the properties of its products. The property rights of third parties must be respected. All orders are accepted in accordance with the terms of our current General Terms and Conditions of Sale and Supply.

Users should be aware of and use the latest and most up-to-date version of the local Product Data Sheets, copies of which will be sent to anyone upon request, or can also be obtained on the www.poliureasistemas.com